# **ULTRACOAT PLUS**

**Acrylic Wall Putty** 



INDICUS ULTRACOAT PLUS is a water based acrylic wall putty for use in interior areas. It's creamy consistency makes it easier to apply and gives a rich and smooth finish.



Rich & smooth finish



**Superior bonding** 



Improves aesthetics



Improves paint performance



INDICUS ULTRACOAT PLUS can be used on plastered walls, AAC walls, asbestos, concrete, ceilings, etc. in internal areas.

## **Technical Properties**

Appearance	Viscous paste
Finish	Matt
Colour	White
Specific Gravity	1.76 ± 0.02
Drying Time*	Touch dry : 30 mins. Recoat : 4 to 6 hours
Full Curing*	6 to 8 hours
Dilution	Not needed. If required, clean water can be added.

### Coverage

Approximately 25 sq.ft. per kg per coat



\* Drying time, full curing and coverage will vary depending upon the surface & climatic condition, degree of dilution and method of application.



#### **Application Procedure**

#### Surface Preparation

- New cementitious surfaces must be properly cured, clean and sound in condition.
- In case of dampness/waterproofing problems, repair the surface using GODRY Waterproofing Solutions.
- Open non-structural cracks, if any, in V-groove and fill with INDICUS EASYSEAL.

#### **Application**

- 1. Moisten the wall with sufficient quantity of clean water.
- 2. Apply one coat of INDICUS ULTRAPRIME wall primer and apply ULTRACOAT PLUS with the help of a putty knife.
- Allow the first coat to dry for 4 to 6 hours and apply a second coat if needed.
- 4. Allow the putty to cure for 6 to 8 hours, preferably overnight.
- 5. Use fine emery paper to remove application marks, if any.
- 6. Apply another coat of INDICUS ULTRAPRIME wall primer and finish with topcoat.

Disclaimer. The product information and applications details given in this data sheet is meant to serve as a general guideline only. Users are advised to undertake a trial for product suitability prior to full-scale usage. There is no express or implied guaranty/warranty for the results. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.

